




KrystalMet Software for Material Testing - KRYSTAL -

Batch Details

Client SUNGREEN - BECIS - JINDAL
Batch GRATING 38 X 38 X 25 - BREAKNG @ 400 MM SPAN
Batch Creation Date 2 October 2021 : 16:56

Superimposed Graph Details



Sr.	Fm(kN)	Displacement at Fm(mm)	Maximum Displacement (mm)	Compression Strength(MPa)	Energy Under Graph Area(J)
1	19.080	34.800	57.300	40595.745	343.472
2	21.120	26.900	28.200	44936.170	329.586
3	19.080	29.400	34.400	40595.745	322.363
Avg.	19.760	30.367	39.967	42042.553	331.807

Tested By

Verified By

Authorised By

Tested On: ARC INSULATION & INSULATORS PVT.LTD.,UTK-60E, Sr. No.2010-1020

KrystalMet:V4R7 - Software for Material Testing - © KRYSTAL

